TEKROK 'C' - Plaster

Tekrok C is a new generation fireproofing plaster for use in the Chemical and Petrochemical Industries. **Terkok C** has recently been modified using advanced chemical technology improving durability and workability.

TYPICAL APPLICATIONS:

- Fire protection of structural steel
- Fire protection of LPG Vessels
- Fire protection of vessel skirts
- Fire protection on cables and junction boxes

APPLICATION:

Tekrok C may be mixed by hand or preferably mechanically for at least 3 minutes. The plaster is then spray applied onto the substrate (steel, concrete gypsum board.) in several passes. Detailed application procedures covering different protective requirements is available on request.

PHYSICAL PROPETIES:

Setting time	Minimum 45 minutes
	Maximum 5.5 hours
Bulk density loose	370 -430 (g/ℓ)
Dry density	800 – 900kg/m³
Strike shuttering	24 hours

The information and recommendations presented on this data sheet are to the best of our knowledge and belief accurate and reliable, but do not constitute a warrant. None of our representatives or agents are authorized to give any guarantee or warrantee or make any representation in addition or contrary to the above, and we not accept liability for claims of any kind for any loss including, without limitation, consequential loss injury or damage arising from the use of the information on recommendation, or of the products which are the subject matter hereof. These products are sold subject to our standard conditions of sale and tender, copies of which are available on request.

TEKROK 'C' - Plaster

Colour	:	Grey
PH	:	12 – 12.5
Shelf life	:	12 months
Storage	:	Keep dry until ready to use
Package	:	20 kg/ bag

SAFETY:

There are no known health hazards and normal precautions relevant to the handling of cement based products applies, i.e. dust masks, eye protection and covering of sensitive skin. **Tekrok C** does not contain asbestos.

The information and recommendations presented on this data sheet are to the best of our knowledge and belief accurate and reliable, but do not constitute a warrant. None of our representatives or agents are authorized to give any guarantee or warrantee or make any representation in addition or contrary to the above, and we not accept liability for claims of any kind for any loss including, without limitation, consequential loss injury or damage arising from the use of the information on recommendation, or of the products which are the subject matter hereof. These products are sold subject to our standard conditions of sale and tender, copies of which are available on request.